

	<b>Product Data Sheet</b>	Issue Date : 01.01.10
<b>Product Name</b>	<b>Futura TexPET- Flame Retardant Type 207</b>	Old Type No. 20105

### Recommended Applications

- ▶ Flame retardant textile/fiber applications.

### Product Features

- ▶ Futura TexPET-Flame Retardant is a polyester based resin containing reactive phosphorous based halogen free flame retardant additive.
- ▶ High standard technology of TiO<sub>2</sub> incorporation ensures excellent polymer characteristics such as filterability, uniform TiO<sub>2</sub> distribution etc.
- ▶ Phosphorous content and Intrinsic Viscosity can be customized as per customer's requirement.

### Properties

Characteristic	Unit	Type 207		Test Method
		B – Y3	SMB – Y3	
Intrinsic Viscosity @ 25°C	dL/g	0.61 ± 0.02	0.61 ± 0.02	FPL-QP-V-20-58
TiO <sub>2</sub> Content	wt. %	Nil	0.03 ± 0.01	FPL-QP-A-20-55-Part-B-XXIV
Phosphorous Content	wt. %	0.60 ± 0.02	0.60 ± 0.02	FPL-QP-S-20-55-Part-B-XV
b*Color (as such)	CIE Lab	4 max.	4 max.	FPL-QP-S-20-55-Part-B-XXI
Carboxyl Number	meq/kg	50 max.	50 max.	FPL-QP-T-20-55-Part-B-VIII
Melting Point	°C	240 ± 3	240 ± 3	FPL-QP-DSC-20-55-Part-B-XVIII #
DEG	wt. %	2.5 max.	2.5 max.	FPL-QP-GC-20-55-Part-B-XIII
Bulk Density	g/cc	0.80 ± 0.10	0.80 ± 0.10	FPL-QP-P-20-55-Part-B-XX
Weight of 20 Chips	mg	570 ± 50	570 ± 50	FPL-QP-W-20-55-Part-A-I
Moisture (when packed)	wt. %	0.25 max.	0.25 max.	FPL-QP-E-20-55-Part-B-VI

# Determined using DSC second heating cycle.

### Packing

Resin can be supplied in 900 kg PP jumbo bags with LDPE liner at 20 bags per 20 ft FCL container as required.

### Contact Address

Futura Polymers, a division of Futura Polyesters Limited, 1-A Kamarajar Salai, Manali, Chennai, India - 600 068.	Tel : + 91 44 25941313 – 17, 25941704 – 05 Fax : + 91 44 25941615, 1054, 1566 e-mail : futurach@futura polyesters.com Web : www.futura polyesters.com
---	--

All products are under continual improvement. Rights are reserved to modify product/process without prior notice subject to performance criteria as per product data sheet