

	Product Data Sheet	Issue Date : 01.01.10
Product Name	Futura PTN – Type 404	Old Type No. 2001

Recommended Applications

- ▶ Applications requiring high CO₂ and O₂ barrier such as:
 - a) Multilayer containers.
 - b) Specialty barrier films.
- ▶ Specialty barrier Sheets for Thermoforming and Vacuum forming applications.

Product Features

- ▶ Futura PTN is Polytrimethylene naphthalate thermoplastic polyester resin.
- ▶ Futura PTN is derived from NDC (dimethyl-2,6-naphthalene dicarboxylate) and PDO (1,3-propane diol) provides improved gas and water vapor barrier properties, enhanced flavor retention and extended shelf life in packaging application.
- ▶ Futura PTN is in full compliance with USFDA regulations for multilayer applications.
- ▶ Futura PTN is recyclable.

Properties

Characteristic	Unit	Type 404		Test Method
		D8	D9	
Intrinsic Viscosity @ 30°C	dL/g	0.65 ± 0.02	0.72 ± 0.02	FPL-QP-V-20-58
b* Color	CIE Lab	1 max.	2 max.	FPL-QP-S-20-55-Part-B-XXI
Melting Point	°C	204 ± 5	204 ± 5	FPL-QP-DSC-20-55-Part-B-XVIII #
Bulk Density	g/cc	0.80 ± 0.10	0.80 ± 0.10	FPL-QP-P-20-55-Part-B-XX
Weight of 20 Chips	mg	300 ± 50	300 ± 50	FPL-QP-W-20-55-Part-A-I
Moisture (when packed)	wt. %	0.25 max.	0.25 max.	FPL-QP-E-20-55-Part-B-VI

Determined using DSC second heating cycle.

Processing Parameters

a) Drying Condition

Granules must be thoroughly dried before processing to limit the occurrence of hydrolytic degradation.

Drying temperature	155 ± 5 °C
Drying time	4- 5 hours
Dew point	- 40 °C
Residual moisture content	≤ 25 ppm

b) Process Temperature (Injection Stretch Blow Molding)**

Barrel Temperature	250 ± 5 °C
Mold Temperature	250 ± 5 °C

** The values quoted above are typical numbers for benchmarking. Individual machine parameters should be determined on a case-by-case depending on the design of the product(s).

Packing

Resin can be supplied in 1000 kg PP jumbo bags with LDPE liner at 20 bags per 20 ft FCL container as required.

Contact Address

Futura Polymers, a division of Futura Polyesters Limited, 1-A Kamarajar Salai, Manali, Chennai, India – 600 068.	Tel : + 91 44 25941313 – 17, 25941704 – 05 Fax : + 91 44 25941615, 1054, 1566 e-mail : futurach@futurapolyesters.com Web : www.futurapolyesters.com
---	--

All products are under continual improvement. Rights are reserved to modify product/process without prior notice subject to performance criteria as per product data sheet